



MICRO POWDERS, INC.

Specialty Micronized Wax Additives

BL-1201: PRESSED POWDER BLUSH WITH MICROEASE 110S (Efficient Binding with Creamy Aesthetics)

INGREDIENT	INCI NAME	% W/W	SUPPLIER
Phase A			
Sericite PHN	Mica	80.75	Presperse
Microease 110S	Synthetic Wax	5.00	Micro Powders, Inc.
Luxsil®	Calcium Aluminum Borosilcate	2.00	Presperse
Red Iron Oxide 7080	Iron Oxide	4.00	Sensient Colors LLC
Titanium Dioxide 3328	Titanium Dioxide	2.00	Sensient Colors LLC
D&C Red #27 Al Lake	D&C Red No. 27 Aluminum Lake	2.00	DeWolf Chemicals
BarGuard™ S	Caprylyl Glycol, Phenoxyethanol & Sorbic Acid	1.00	Hampford Research Inc.
Phase B			
Xiameter PMX-200, 50CST	Dimethicone	3.00	Dow Corning
Vitamin E Acetate	Tocopherol Acetate	0.25	BASF
	Total	100%	

Procedure

1. Combine all ingredients in the order listed, mixing well before each addition.
Add Phase B mix well until uniformly dispersed.
2. Pass through a micropulverizer until color is evenly dispersed.
3. Press at 2000 Psi.