



MICRO POWDERS, INC.

Specialty Micronized Wax Additives

ES-1314: OIL-FREE PRESSED POWDER EYE SHADOW WITH NATURESOFT 860R (Naturesoft 860R provides superior dry binding and silky aesthetics)

INGREDIENT	INCI NAME	% W/W	SUPPLIER
Phase A			
Sericite PHN	Mica	39.65	Presperse
Zinc Stearate	Zinc Stearate	5.00	N/A
Ultramarine Blue 7104	Ultramarine Blue	1.00	Sensient Colors LLC
Cosmetic Green CGI-1245	Chromium Oxide Green	12.50	Sun Chemical
Black Iron Oxide 7133	Iron Oxide Black	0.50	Sensient Colors LLC
Yellow Iron Oxide 7055	Iron Oxide Yellow	1.00	Sensient Colors LLC
BarGuard™ S	Caprylyl Glycol, Phenoxyethanol & Sorbic Acid	1.00	Hampford Research Inc.
Naturesoft 860R	Rice Bran Wax	30.00	Micro Powders, Inc.
Phase B			
Prestige Green	Mica & TiO ₂ & Iron Oxide	10.00	Eckart
Phase C			
Xiameter PMX-200, 50CST	Dimethicone	2.50	Dow Corning
Vitamin E Acetate	Tocopherol Acetate	0.25	BASF
	Total	100%	

Procedure

1. Combine Phase A ingredients in a suitable blender and mix until uniform.
2. Pulverize through a 0.20" herringbone screen.
3. Return Phase A to the blender and add phase B + C. Mix until uniform.
4. Pass the combined phases through a pulverizer equipped with 0.062" herringbone screen.
5. Press at 1500 Psi in an appropriate container.

Micro Powders, Inc. 580 White Plains Road, Tarrytown, NY 10591 Tel: (914) 793-4058 Fax: (914) 472-7098
www.mpipersonalcare.com