



## AquaPoly 215

Micronized oxidized polyethylene for rub resistance and slip in aqueous systems

### Features and Benefits

- Provides good rub and mar resistance
- Improves slip properties
- Imparts antiblocking
- Economical

### Composition

Oxidized polyethylene

### Recommended Addition Levels

0.5-2.0% (on total formula weight)

### Systems and Applications

Water based coatings. Industrial coatings (including wood and metal); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); seed coatings.

### Typical Properties\*

	<u>AquaPoly 215</u>	<u>AquaPoly 215F</u>	<u>AquaPoly 215VF</u>
<b>Melting Point °C</b>	105 - 111	105 - 111	105 - 111
<b>Density @ 25 °C (g/cc)</b>	0.94	0.94	0.94
<b>NPIRI Grind</b>	5.0 - 6.0	3.0 - 4.0	2.0 - 3.5
<b>Maximum Particle Size (µm)</b>	31.00	26.16	22.00
<b>Mean Particle Size (µm)</b>	9.0 - 11.0	6.0 - 8.5	5.0 - 7.5

AquaPoly 215 is also available as a water based wax dispersion - Microspersion 215-50. AquaPoly 215F and 215VF ARE MADE TO ORDER PRODUCTS WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Aug-21

### Micro Powders, Inc.

580 White Plains Road, Tarrytown, NY 10591  
TEL 914.793.4058 FAX 914.472.7098  
Email: mpi@micropowders.com

\*The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.