

micropowders.com

# Microspersion<sup>®</sup> 123AL-40

A nonionic water based dispersion of a highly engineered LDPE/aluminum oxide nanocomposite for unsurpassed scratch and scuff resistance

#### **Features and Benefits**

. . . . . . . . . . . . .

- Convenient, ready-to-use, pourable nonionic wax dispersion
- Maximum scratch and abrasion resistance for antislip surfaces
- LDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- · Provides excellent antiblocking properties
- Does not lower COF like high density polyethylene grades
- Composite wax/aluminum oxide particle is less abrasive on processing equipment compared to free aluminum oxide

Microspersion 123AL-40

## **Dry Wax ID**

MPP-123AL

### **Recommended Addition Levels**

2.0-5.0% (on total formula weight)

### **Systems and Applications**

Water based coatings and inks. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); floor coatings.

#### **Typical Properties\***

Wax Solids	40%
Viscosity @ 25 °C (cP)	5,000 - 9,000
рН	9.0 - 10.5
Density @ 25 °C (g/cc)	0.98
Wax Mean Particle Size (µm)	9.5 - 12.5
NPIRI Grind	4.0 - 6.0

Mar-23

#### Micro Powders, Inc.

580 White Plains Road, Tarrytown, NY 10591 Tel: (914) 793-4058 | micropowders.com \*The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.